

Order group	Carrier material as per DIN 1614 or 17100	Zinc Coating*
Z 150 150 g/m ² min. coating	StW 22 St 37-2	150 g/m ² 20 My
Z 225 150 g/m ² min. coating	St 33 St 37-2 StW 22	225 g/m ² 30 My
Z 300 150 g/m ² min. coating	St 33 St 37-2 StW 22	300 g/m ² 40 My
Z 500 150 g/m ² min. coating	St 33 St 37-2 StW 22	500 g/m ² 70 My

* Min. zinc coating thickness in g/m² per free surface

If you require other steel qualities or zinc coatings, please get in touch with us direct.

Nominal width	Nominal thickness	Nominal width tolerance	Nominal thickness tolerance	
15 - < 100 mm	1.0 - < 2.0 mm 2.0 - < 4.0 mm 4.0 - 6.0 mm	+0.8 mm +0.8 mm +0.8 mm	+/-0.15 mm +/-0.17 mm +/-0.19 mm	-0.15 +0.21 mm -0.17 +0.23 mm -0.19 +0.25 mm
100 - 125 mm	1.0 - < 2.0 mm 2.0 - < 4.0 mm 4.0 - 6.0 mm	+0.8 mm +0.8 mm +0.8 mm	+/-0.18 mm +/-0.20 mm +/-0.22 mm	-0.18 +0.24 mm -0.20 +0.26 mm -0.22 +0.28 mm
			Zinc coating 150/225 g/m ²	Zinc coating 300/500 g/m ²

For other tolerances please get in touch with us direct.

Options

Area of application _____

Dimension Thickness _____ [mm]
Width _____ [mm]

Edges Slitted edge strip Rounded edge strip

Steel Quality StW 22 St 33
 St 37-2

Zinc Coatings Z 150 Z 300
 Z 225 Z 500

Coil dimensions Coil weight _____ [kg]
Coil outer dimensions _____ [mm]
 with welded joint without welded joint

Rods Rod length _____ [mm]

Bundles Crane bundle weight _____ [kg]

Zinc Coatings Standard Disposable pallet
 Flat stack Europallet

Company: _____

Contact person: _____

Address: _____

City / Postcode _____

Phone: _____

Fax: _____

Please fax any price queries to our sales office. We would be pleased to make you a nonbinding offer.

Sales
Gebr. MEISER GmbH
Edmund Meiser Straße 1
66839 Schmelz-Limbach
Telephone + 49 (0) 6887 309 1919
Facsimile + 44 (0) 6887 309 3939
Email info@meiser.de

Production
Bandverzinkung St. Ingbert
Alleestraße 5
66386 Sankt Ingbert
Phone + 49 (0) 6894 92146-0
Facsimile + 49 (0) 6894 92146-20
Email info@meiser.de

MEISER
www.meiser.de



Strip Coating Processes:
MEISER provides everything
under one roof.

Raw Stock

Slitted edge strip:

Rolled from hot wide strip and then cut to the nominal dimensions specified. The edges are slightly sharp and brittle.

Rounded edge strip:

The same process as with the slitted edge strip except that the edges are then rounded off by machining or cutting means.

Dimensions Programme:

- Width 15.00 < 40.00 mm
Thickness 1.00 < 6.00 mm
- Width 40.00 < 80.00 mm
Thickness 1.00 < 5.00 mm
- Width 80.00 < 110.00 mm
Thickness 1.00 < 4.00 mm

Other measurements available on request. Just give us a call or contact us.

Zinc Coatings

The main influence on processability in general and ductility in particular is the thickness of the zinc coating.

Z 150

For special requirements in terms of ductility and the manual or mechanical production of sections, design components, cable harnesses and channel holders.

Z 225

For standard requirements in terms of corrosion protection and relatively straightforward shape-forming – e.g. fittings and fixtures, wide angles and U-shaped-sections, clamps, clips, cable ways, cable guides, packing straps and barrel hoops etc.

Z 300 und Z 500

For special and/or enhanced corrosion protection requirements with less emphasis on ductility. For lightning conductors and earth connections.

Tolerances

• In the thickness

Nominal thickness is defined as the thickness of the finished hot galvanised band steel i.e. the thickness of the carrier material including the zinc coat.

• In the width

Nominal width is defined as the width of the finished hot galvanised band steel i.e. the thickness of the carrier material including the zinc coat of the longitudinal sides.

Options

Coil inner diameter

ca. 500 mm (standard)

Coil outer diameter

Please specify desired measurement on ordering.

Without welded joint

Coil weights not optional but short lengths possible.

With welded joint

Suitable for machining but with restrictions. Coil weight can be specified but with a minimum weight of 20 kg and a maximum outer diameter of 1250 mm.

Coils in metre lengths

Please contact us direct.

Ties

- above 50 kg in weight 3x signode tape 1/2"
- under 50 kg in weight 2x signode tape 1/2"

Bundles

Combined as a crane ready bundle, weight usually 1000 kg per bundle minimum.

Shipping

- Standard – horizontal axis
- Flat stacked on wooden bases
- Flat stacked on disposable pallets
- Europallets on an exchange basis

An extra charge is made for wooden spacers between the rings.

Rods

Available in lengths of anything between 1000 and 7000 mm (standard) Length tolerance: -0+50 mm
Other lengths and tolerances by agreement.

